



Andrews, David

From: GJRig02@oxy.com
Sent: Sunday, October 10, 2010 2:06 PM
To: Andrews, David
Cc: Brad_Ahlquist@Oxy.com; Simon_Benevides@oxy.com; Ronald_Bevans@oxy.com; OB_Sanchez@oxy.com; Dmitry_Smushkov@oxy.com; Victor_Guerra@oxy.com
Subject: CEMENT SURFACE 697-15-19A

Follow Up Flag: Follow up
Flag Status: Flagged

Mr. Andrews,

H&P 353 9-5/8" CEMENT SURFACE CASING DEPTH 2434' (API 05-045-18027-00) TESTED LINES TO 2560 PSI.

PUMPED 20 BBLS FRESH WATER, 20 BBLS OF SUPER FLUSH, 20 BBLS OF FRESH WATER.

CMT 9-5/8" SURFACE CSG WITH:

891 SKS - 369 BBLS OF 12.3 PPG-2.33 CU. FT/SK VERSACEM LEAD WITH TUFF FIBER, 134 SKS- 50 BBLS OF 12.8 PPG-2.07 CU. FT/SK VERSACEM TAIL.

FULL RETURNS THROUGHTOUT CMT JOB.

DISPLACED WITH 184.2 BBLS FREACH WATER AT 6 BPM.. OBSERVED 700 PSI LIFT PRESSURE AT 2 BPM. BUMPED PLUG WITH 1340 PSI. FLOATS HELD.CIRCULATED 100 BBLS OF CEMENT TO SURFACE FLUSHED PARASITE LINE WITH 10 BBLS SUGUR WATER H2O HAD RETURNS AFTER 5 BBLS. PRESSURE SPIKE AT 215 PSI CEMENT FELL 100', TOP OUT WITH 15 BBLS OF 12.5 PPG- 1.97 CU.FT/SK