



Andrews, David

From: GJRig02@oxy.com
Sent: Tuesday, August 09, 2011 12:05 PM
To: Kellerby, Shaun; Brad_Ahlquist@Oxy.com; Amrut_Athavale@oxy.com;
Simon_Benevides@oxy.com; Longworth, Mike; Nicolas_Carestia@oxy.com;
Daniel_Padilla@oxy.com; Sallie_Phay@oxy.com; Joan_Proulx@oxy.com
Cc: Andrews, David
Subject: OXY/H&P353/CC-697-16-29B/CC-697-16-28PAD CEMENT SUMMARY

9.625" CASING DEPTH ~~2,92~~ *2692' D.A.*
API # 05-045-20574-00

PUMPED 20 BBLS FRESH WATER, 20 BBLS OF FRESHWATER WITH GEL, 20 BBLS OF FRESH WATER.
CMT 9-5/8" 36# J-55 SURFACE CASING WITH:
1050 SKS - 435.7 BBLS OF 12.3 PPG-2.33 CU. FT/SK VERSACEM LEAD, 150 SKS- 55.3 BBLS OF 12.8 PPG-2.07 CU.
FT/SK VERSACEM TAIL. 50% EXCESS DISPLACED WITH 204.6 BBLS FRESH WATER AT 6 BPM. OBSERVED 440
PSI LIFT PRESSURE AT 2 BPM.
BUMPED PLUG 940 PSI. FLOATS HELD.
HAD NO RETURNS DURING CEMENT JOB
TOTAL CEMENT TO SURFACE 0 BBLS.
TEST 9-5/8" CASING TO 1,500 PSI FOR 30 MINUTES PASSED TEST.

FLUSHED PARASITE LINE WITH 10 BBLS SUGAR WATER HAD RETURNS AFTER 2 BBLS. PRESSURE SPIKE AT
450 PSI. HAD WATER BACK AT 6.0 BBLS.

TOP OUT OFF LINE WITH: 94.2 BBLS WITH 5 BBLS TO SURFACE.

Alex Villegas - DSM
OXY USA
H&P 353
DIRECT:281-436-6464